



W. R. MEADOWS

SEALTIGHT

DATA SHEET NO. 7100-201A

VIBRAFLEX® MTO
Waterproofing Protection Board

DESCRIPTION

VIBRAFLEX MTO waterproofing protection board is a semi-flexible core board, composed of a mineral-fortified asphaltic core between two outside layers consisting of an asphalt impregnated fibreglass mat and manufactured specifically to conform with the Ontario Ministry of Transportation specifications.

USES

VIBRAFLEX MTO protects hot-applied rubberized asphalt bridge deck waterproofing membranes from damage by construction traffic and during the application of asphaltic or Portland cement concrete overlays.

FEATURES/BENEFITS

- Absorbs the impact of placing concrete or asphalt overlays and normal job site traffic on waterproofed slabs.
Protects membrane from penetration by sharp aggregates.

PACKAGING

0.9 m (3') x 1.5 m (5') Sheets
1.2 m (4') x 1.5 m (5') Sheets

STANDARDS

Ministry of Transportation, Ontario approved
O.P.S.S. 1215, O.P.S.S. 914. D.S.M. 9.90.60

TECHNICAL DATA

Testing to OPSS 1215

Table with 2 columns: Property and Value. Rows include Thickness (3.6 mm ± 0.4 mm), Width (1000 mm ± 150 mm), Length (1500 mm ± 150 mm), Puncture (None), Indentation (<0.9 mm, Pass), Compatibility (Pass), Bond (Pass), and Water Absorption (Less than 5%, Pass).

APPLICATION

Install to form a continuous protective layer over the membranes in accordance with OPSS 914. Sheets are easily cut to fit with a roofer's knife. Protection board shall be laid on the asphalt membrane while the surface is still tacky, with the length of the board transverse on the deck. Materials or substances shall not be applied to the membrane surface to remove the tackiness prior to installation of the protection board.

Application Method ... The protection board shall be placed with edges overlapping 12.7 - 25.4 mm both longitudinally and transversely. The protection board edge shall be within 6 mm of all curbs, drain verticals, and expansion joint verticals. Protection board shall be placed such that the longitudinal (direction of traffic flow) joints are staggered a minimum of 150 mm.

Tack coat material shall be applied to the protection board cover with approved equipment which will provide a uniform application at the required rate. The tack coat shall be applied only when the protection board is clean and dry. The tack coat on the protection board cover shall be placed just sufficiently ahead of paving to allow for curing. The diluted tack coat material shall be applied at the rate of 0.5 litre/m².

Binder course pavement shall be placed within one week of waterproofing. Paving equipment shall not be permitted on the tack coat until it has fully cured.

PRECAUTIONS

Read and follow application information, precautions, and Safety Data Sheet.

MASTERFORMAT NUMBER AND TITLE

07 10 00 - Dampproofing and Waterproofing

W. R. MEADOWS® OF CANADA
70 Hannant Court, Milton, ON L9T 5C1
21 Streambank Ave., Sherwood Park, AB T8H 1N1
(800) 342-5976
Montreal Sales: (514) 865-2406

Hampshire, IL / Cartersville, GA / York, PA / Fort Worth, TX
Benicia, CA / Pomona, CA / Goodyear, AZ / Milton, ON
Sherwood Park, AB
www.wrmeadows.com
info@wrmeadows.com

LEED INFORMATION

May help contribute to LEED credits:

- MRc9: Construction and Demolition Waste Management

2019-03-07

