



DATA SHEET NO. 3300-131

1220-WHITE Pigmented Curing Compound

DESCRIPTION

1220-WHITE pigmented curing compound is a waterborne, resin-based curing compound containing suspended white pigment. It permits complete hydration of the cement by retaining at least 97% of the water present in the concrete at the time of application for at least seven days. The white pigment reflects the heat-producing rays of the sun, keeping concrete surfaces cooler and preventing excessive heat build-up and resultant thermal cracking during the curing period.

USES

1220-WHITE is a reflective curing compound designed for exterior use on freshly placed concrete surfaces, both horizontal and vertical, particularly where protection from the sun's heat is required. It is recommended for use on driveways, walls, sidewalks, concrete highways, runways, overpasses, bridges, tunnels, etc.

FEATURES/BENEFITS

- 1220-WHITE pigmented curing compound contains SUSPENSOID, a unique additive which assists pigment dispersion and prevents excessive pigment settlement.
- Excellent moisture retention properties.
- Excellent heat reflective properties.
- Excellent sprayability.
- Easy clean up.

PACKAGING

18.9 Litre Pail
205 Litre Drum

COVERAGE

4.9 m²/litre (240 ft.²/gal.)

SHELF LIFE

When stored indoors in original, unopened containers at temperatures between 4° - 32° C, optimum performance and best use is obtained within one year of date of manufacture.

SPECIFICATIONS

- ASTM C 309, Type 2, Class A and B
- Complies with Canada VOC Concentration Limits for Architectural Coatings Regulations.
- OPSS 904 - MTO D.S.M. 9.25.25 Form 1315 - Ministry of Transport, Ontario
- Approved by the Ministry of Transportation, Quebec.

APPLICATION

Mixing ... Only nominal agitation of 1220-WHITE is required prior to each use. Do not employ constant re-circulating pumps or high-speed mixers.

Application Method ... Apply in a uniform film to horizontal surfaces as soon as the surface water disappears and the surface will not be marred by walking workmen. On vertical surfaces, apply promptly after the forms are removed. 1220-WHITE may be applied with a typical commercial hand or power sprayer, such as a Chapin 1949. Use a spray nozzle that produces a flow of 1.9 LPM under .276 MPa of pressure. Do not allow the spray nozzle to drip.

Drying Time ... Restrict foot traffic for at least four hours. Drying times may be extended depending on application rate, temperature, humidity, and project conditions.

Clean Up ... Clean tools and equipment immediately after use with water. Once dried, material would need to be cleaned with xylene, toluol, or SEALTIGHT® SOLVENT from W. R. MEADOWS.

Continued over...

W. R. MEADOWS® OF CANADA
70 Hannant Court, Milton, ON L9T 5C1
Phone: (905) 878-4122 • Fax: (905) 878-4125
Montreal Sales: (514) 865-2406

Hampshire, IL / Cartersville, GA / York, PA / Fort Worth, TX
Benicia, CA / Pomona, CA / Goodyear, AZ / Milton, ON
Sherwood Park, AB
www.wrmeadows.com

PRECAUTIONS

Do not apply when air, material and/or surface temperatures are expected to fall below 4° C within four hours of completed application. 1220-WHITE is not recommended for use on concrete surfaces that are later to be painted, tiled, hardened, sealed, or treated in any manner. Avoid breathing vapours. Avoid prolonged contact with skin. **FOR INDUSTRIAL USE ONLY.**

MASTERFORMAT NUMBER AND TITLE

03 39 23 – Membrane Concrete Curing

For most recent data sheet, LEED information, and SDS, visit www.wrmeadows.com

2015-03-19



© SEALTIGHT is a registered trade mark of W. R. Meadows

WARRANTY: W. R. Meadows of Canada warrants that, at the time and place we make shipment, our materials will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM OF TRADE OR OTHERWISE. As the exclusive remedy for breach of this Warranty, we will replace defective materials, provided, however, that the buyer examine the materials when received and promptly notify us in writing of any defect before the materials are used or incorporated into a structure. Three (3) months after W. R. Meadows of Canada has shipped the materials, all our Warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates and no action for breach of any such duties may thereafter be commenced. W. R. Meadows of Canada shall in no event be liable for consequential damages. Unless otherwise agreed to in writing, no warranty is made with respect to materials not manufactured by W. R. Meadows of Canada. We cannot warrant or in any way guarantee any particular method of use or application or the performance of materials under any particular condition. Neither this Warranty nor our liability may be extended or amended by our salesmen, distributors or representatives, or by our distributor's representatives, or by any sales information or drawings.